

Appln No. 09/710,490

Amdt date October 22, 2003

Reply to Office action of March 12, 2003

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Canceled)
2. (Previously presented) The negative active material slurry composition of claim ~~6~~ wherein the transition metal is selected from the group consisting of Mn, Ni, Fe, Cr, Co, Cu and Mo, the alkaline earth metal is selected from the group consisting of Ca and Mg, and the semi-metal is selected from the group consisting of B, Al, Ga, Si and Sn.
3. (Canceled)
- 3 ~~4~~. (Previously presented) The negative active material slurry composition of claim ~~6~~ wherein the compound includes at least one boron compound.
5. (Canceled)
- 1 ~~6~~. (Currently Amended) A negative active material slurry for a rechargeable lithium battery comprising a mixture of a carbonaceous negative active material and a compound in an organic solvent, the compound being selected from the group consisting of nitride compounds[,], and chloride compounds [~~and fluoride compounds~~], wherein the compound further comprises at least one element selected from the group consisting of transition metals, alkaline metals, alkaline

Appln No. 09/710,490

Amdt date October 22, 2003

Reply to Office action of March 12, 2003

earth metals and semi-metals, wherein the amount of the compound is 0.05 to 30 wt %.

7. (Canceled)

5 8. (Previously presented) The method of claim 12 wherein the transition metal is selected from the group consisting of Mn, Ni, Fe, Cr, Co, Cu and Mo, the alkaline metal is selected from the group consisting of Na and K, the alkaline earth metal is selected from the group consisting of Ca and Mg, and the semi-metal is selected from the group consisting of B, Al, Ga, Si and Sn.

9. (Canceled)

6 10. (Previously presented) The method of claim 12 wherein the compound includes at least one boron compound.

11. (Canceled)

4 12. (Currently Amended) A method of manufacturing a negative electrode for a rechargeable lithium battery comprising:

mixing a carbonaceous negative active material with a compound to form a mixture, the compound being selected from the group consisting of nitride compounds[,] and chloride compounds [~~and fluoride compounds~~], wherein the compound further comprises at least one element selected from the group consisting of transition metals, alkaline metals, alkaline earth metals and semi-metals, wherein the amount of the compound is 0.05 to 30 wt %;

adding an organic solvent to the mixture;

Appln No. 09/710,490

Amdt date October 22, 2003

Reply to Office action of March 12, 2003

coating the resulting mixture on a current collector; and
drying the coated current collector and pressing the dried current collector.

13. (Canceled).